

WH

### Induction hardened and ground hollow linear shafts

#### Dimensions

OD: Ø12 - 60 mm

#### Surface hardness

63±2 HRC

#### Surface roughness

Ra max. 0.20 µm

#### Standard indicative length

6400 (-0/+50) mm  
other, on request

#### Surface hardening depth, SHD

according to EN ISO 15787

#### On request

special lengths, tolerances and dimensions

### Chemical composition - in % by weight

Steel grade	C	Si	Mn	P	S	Cr	Ni	Mo	V
C60E	0.57 ÷ 0.65	0.10 ÷ 0.40	0.60 ÷ 0.90	max. 0.025	max. 0.035	max. 0.4	max. 0.4	max. 0.1	-

### Mechanical properties

Steel grade	Tensile strength	Yield strength	Elongation
	R <sub>m</sub> N/mm <sup>2</sup>	R <sub>p0.2</sub> N/mm <sup>2</sup>	A <sub>5</sub> %
C60+NBK	720 - 900	min. 390	min. 13

NBK = normalized in a protective atmosphere.


### Steel grades correspondences

EN	Werkstoff	DIN	B.S.	UNI	JIS	GOST	AISI / SAE / ASTM
C60E	1.1221	Ck60	060A62, 070M60	C60	S58C	60, 60G, 60GA	1060

### NI-WH / Metric

Series	Outside diameter	Inside diameter	Surface hardening depth	Roundness	Parallelism	Straightness	Standard tolerance
	OD mm	ID mm	SHD (min. + tol.) mm	t <sub>1</sub> max. µm	t <sub>2</sub> max. µm	t <sub>3</sub> max. mm/m	ISO h6 µm
NI-WH 12x4	12	4	0.4 + 0.4	5	8	0.20	0 / -11
NI-WH 12x7	12	7	0.4 + 0.4	5	8	0.20	0 / -11
NI-WH 16x7	16	7	0.4 + 0.4	5	8	0.20	0 / -11
NI-WH 20x14	20	14	0.6 + 0.5	6	9	0.20	0 / -13
NI-WH 25x15	25	15	0.8 + 0.8	6	9	0.15	0 / -13
NI-WH 30x18	30	18	0.9 + 0.8	6	9	0.15	0 / -13
NI-WH 40x28	40	28	1.2 + 1.1	7	11	0.15	0 / -16
NI-WH 40x26	40	26	1.2 + 1.1	7	11	0.15	0 / -16
NI-WH 50x30	50	30	1.5 + 1.2	7	11	0.15	0 / -16
NI-WH 60x36	60	36	1.5 + 1.2	8	13	0.15	0 / -19

WH



### Dimensions

OD:  $\emptyset 5/8'' - 2''$

### Surface hardness

63±2 HRC

### Surface roughness

Ra max. 0.20  $\mu\text{m}$

### Standard indicative length

6400 (-0/+50) mm / 251.96 (-0/+2)''  
other, on request

### Surface hardening depth, SHD

according to EN ISO 15787

### On request

special lengths, tolerances and dimensions

## Chemical composition - in % by weight

Steel grade	C	Si	Mn	P	S	Cr	Ni	Mo	V
C60E	0.57 ÷ 0.65	0.10 ÷ 0.40	0.60 ÷ 0.90	max. 0.025	max. 0.035	max. 0.4	max. 0.4	max. 0.1	-

## Mechanical properties

Steel grade	Tensile strength	Yield strength	Elongation
	$R_m$ N/mm <sup>2</sup>	$R_{p0.2}$ N/mm <sup>2</sup>	$A_5$ %
C60+NBK	720 - 900	min. 390	min. 13

NBK = normalized in a protective atmosphere.

## Steel grades correspondences

EN	Werkstoff	DIN	B.S.	UNI	JIS	GOST	AISI / SAE / ASTM
C60E	1.1221	Ck60	060A62, 070M60	C60	S58C	60, 60G, 60GA	1060

## NI-WH / Imperial

Series	Outside diameter OD		Inside diameter ID		Surface hardening depth SHD (min. + tol.) inch	Roundness $t_1$ max. inch	Parallelism $t_2$ max. inch	Straightness $t_3$ max. inch/ft	Standard tolerance Class "L" inch
	mm	inch	mm	inch					
NI-WH 15.875x6.35	15.875	0.625	6.35	0.25	0.024 + 0.020	0.000197	0.000315	0.00246	-0.0005 / -0.001
NI-WH 19.05x11.125	19.05	0.75	11.125	0.438	0.035 + 0.032	0.000236	0.000354	0.00246	-0.0005 / -0.001
NI-WH 25.4x15.494	25.4	1	15.494	0.61	0.035 + 0.032	0.000236	0.000354	0.00185	-0.0005 / -0.001
NI-WH 31.75x18.288	31.75	1.25	18.288	0.72	0.035 + 0.032	0.000236	0.000354	0.00185	-0.0005 / -0.001
NI-WH 38.1x22.606	38.1	1.5	22.606	0.89	0.047 + 0.043	0.000276	0.000433	0.00185	-0.0006 / -0.0011
NI-WH 50.8x31.75	50.8	2	31.75	1.25	0.059 + 0.043	0.000276	0.000433	0.00185	-0.0006 / -0.0013